

DESCRIPTION

Total thickness	EN 428	mm	2.10
Thickness of wearlayer	EN 429	mm	0.70
Weight	EN 430	g/m ²	2235
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	Approx 20

CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34-43
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	<2
Slip resistance wet : ramp test with oil	DIN 51 130	class	R9

PERFORMANCE

Wear resistance	EN 660.2	mm ³	≤2.0
Wear group	EN 653	-	T
Dimensional stability	EN 434	%	≤0.40
Residual indentation	EN 433	mm	≤0.05
Impact sound insulation	EN ISO 717-2	dB	8
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥6
Chemical products resistance	EN 423	-	Good
Bacteriostatic and fungistatic treatment	-	-	Sanosol®
Surface treatment	-	-	PUR

CE MARKING

	EN 14041	-	   
--	----------	---	---